



BRILL® 混合粘度チャート

12.5W-40 × 17.5W-50

12.5W-40比率	17.5W-50比率	40°C粘度mm ² /s	100°C粘度mm ² /s	混合後 粘度グレード
100	0	88.3	13.4	12.5W-40
95	5	90.5	13.7	12.5W-40
90	10	92.7	14.0	12.5W-40
85	15	95.0	14.3	12.5W-40
80	20	97.4	14.5	12.5W-40
75	25	99.8	14.8	12.5W-40
70	30	102.2	15.2	12.5W-45
65	35	104.7	15.5	12.5W-45
60	40	107.3	15.8	15W-45
55	45	109.9	16.1	15W-45
50	50	112.6	16.4	15W-45
45	55	115.4	16.8	15W-45
40	60	118.2	17.1	15W-45
35	65	121.0	17.5	15W-45
30	70	123.9	17.8	15W-45
25	75	126.9	18.2	15W-45
20	80	130.0	18.6	17.5W-50
15	85	133.1	18.9	17.5W-50
10	90	136.3	19.3	17.5W-50
5	95	139.6	19.7	17.5W-50
0	100	142.9	20.1	17.5W-50