



BRILL® 混合粘度チャート

17.5W-50 × 20W-60

17.5W-50比率	20W-60比率	40°C粘度mm ² /s	100°C粘度mm ² /s	混合後 粘度グレード
100	0	142.9	20.1	17.5W-50
95	5	144.6	20.3	17.5W-50
90	10	146.4	20.5	17.5W-50
85	15	148.2	20.7	17.5W-50
80	20	150.0	20.9	17.5W-50
75	25	151.8	21.1	20W-50
70	30	153.7	21.3	20W-50
65	35	155.5	21.5	20W-50
60	40	157.4	21.7	20W-55
55	45	159.4	21.9	20W-55
50	50	161.3	22.1	20W-55
45	55	163.3	22.3	20W-55
40	60	165.3	22.5	20W-55
35	65	167.3	22.7	20W-55
30	70	169.3	22.9	20W-55
25	75	171.4	23.1	20W-55
20	80	173.5	23.4	20W-60
15	85	175.6	23.6	20W-60
10	90	177.7	23.8	20W-60
5	95	179.9	24.0	20W-60
0	100	182.1	24.3	20W-60